



Perfecto XEP

Premium Antiwear Turbine Lubricant

Description

Perfecto XEP are turbine oils of highest quality with extremely hydrogen-treated base oils. They contain additives which increase the resistance to aging, improve the corrosion protection properties as well as suppress the foaming tendencies. They also contain antiwear additives to give additional load carrying properties. The additives in the Perfecto XEP oils contain no metal-organic compounds like organic zinc compounds. The superior resistance to oxidation & thermal degradation provides a very long life lubricant because of low deposit / lacquer formation.

Application

The turbine oils Perfecto XEP are preferred for the lubrication of steam and gas turbines and their control systems. The oil supply mostly take place on a common circuit. The oils meet the requirements "Schmier- und Regleröle L-TGP mit Verschleißschutz" according to DIN 51 515 part 2, BS 489 and ISO 8068 "Lubricating Oils for Turbines, categories L-TSA and L-TGA" and the specifications and requirements of the turbine manufacturers which prescribe turbine oils with antiwear properties for the usage in their gear turbines:

- Siemens AG-Power Generation TLV 9013 04 (gas- & steam turbines)
- Alstom Power Generation HTGD 90 117 D
- General Electric GEK 107395
- General Electric GEK 32568F
- General Electric GEK 101941

Features / Benefits

- High chemical and thermal stability means low aging even at longer operating life
- Good viscosity temperature behavior enables to start cold machines without problems and ensures reliable lubrication even at high operating temperatures
- Good air release
- Excellent foaming characteristic, fast foam break-down
- Good corrosion protection, even with condensation and possible water contamination
- Good water demulsification ensures rapid separation of water and oil at water contamination without emulsification
- Neutral behavior against sealing materials and non-ferrous metals
- Good antiwear properties even at high temperature

Typical Physical Characteristics

Test	Method	Unit	Perfecto XEP 32	Perfecto XEP 46	Perfecto XEP 68
Viscosity Grade	ISO 3448	-	ISO VG 32	ISO VG 46	ISO VG 68
Colour	DIN ISO 2049	-	L1,0	L1,0	L1,0
Density (15°C)	DIN 51757	kg/m ³	867	868	869
Viscosity (40°C)	DIN 51562	mm ² /s	32	46	68
Viscosity (100°C)	DIN 51562	mm ² /s	5,7	7,1	9,5
Viscosity Index	DIN ISO 2909	-	112	112	112
Pour Point	DIN ISO 3016	°C	-15	-15	-12
Neutralisation Number	DIN 51558	mg KOH/g	0,10	0,10	0,10
Ash	DIN EN ISO 6245	%	<0,01	<0,01	<0,01
Foam - Sequence 1 (25°C) Tendency / Stability after 10 minutes	ISO 6247	ml	<100 / 0	<100 / 0	<100 / 0
Foam - Sequence 2 (95°C) Tendency / Stability after 10 minutes	ISO 6247	ml	<100 / 0	<100 / 0	<100 / 0
Foam - Sequence 3 (25°C after 95°C) Tendency / Stability after 10 minutes	ISO 6247	ml	<100 / 0	<100 / 0	<100 / 0
Air Release (50°C)	DIN ISO 9120	min.	3	4	5
Water Seperability	DIN 51589	s	<100	<100	<100
Copper Corrosion (3h at 100°C)	DIN EN ISO 2160	degree of corrosion	1a	1a	1a
Rust Test - steel Procedure A (deionized water)	DIN ISO 7120	degree of corrosion	0	0	0
Rust Test - steel Procedure B (seawater)	DIN ISO 7120	degree of corrosion	0	0	0
FZG Gear Failure Load Stage (A/8,3/90)	DIN ISO 14635-1	-	9	10	10
Aging TOST Test: Time to increase 2,0 mg KOH/g	ASTM D 943	hours	>10000	>10000	>10000

Packaging and Storage

All packages should be stored under cover. Where outside storage is unavoidable drums should be laid horizontally to avoid the possible ingress of water and the obliteration of drum markings. Products should not be stored above 60°C, exposed to hot sun or freezing conditions.

Perfecto XEP

07 Oct 2011

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

BP Europa SE, Geschäftsbereich Industrieschmierstoffe , Erkelenzer Str. 20, 41179 Mönchengladbach
Tel: +49 (0)2161 909-30 Fax: +49 (0)2161 909-481
www.castrol.com